


PRIVECY SCREEN PROTECTOR

P/N: DXO-4290-S000



◆ Product Structure


	→50±1u	PE film
	→120±5u	Matte Hard Coat
	→160±10u	Basic layer
	→120±5u	HD PET
	→50±1u	PE film

◆ Product Data

Item	Unit	Value	Remark
Base Film Thickness	mm	0.4±0.02	
Total Thickness	mm	0.5±0.02	
Adhesion(G/50MM)	g	0	
Gluewater deviate Test	----	PASS	Without glue
Rigidity Test(500g)	h	3.9—4.2	
Local diaphaneity Test	----	100/100	
Diaphaneity Test	----	65±5%	
UV Rejection	%	65%	
IR Rejection	%	49%	
Transparency	%	65±5%	

◆ Note

1. The product should be packed well and stored up in the cool dry environment, avoiding straight sunshine freezing and High temperature.
2. Sticking surface should be clean, smooth, dry, no fat or other pollutant.
3. The technical data are based on the reliable experiment carried by the company, whichever are not to guarantee as specified there in Kindly study your purpose and condition to use this product previously in detail upon your own responsibility.



Blue-Light Film Transmittance

